



PYROFIL™ TR50S 15K

Typical Fiber Properties

Tow Tensile	Strength	710 4,900	ksi MPa	JISR 7601
	Modulus	35 240	msi GPa	
Typical Density		0.066 1.82	lb.in ³ g/cm ³	JISR 7601
Typical Yield	15K	496 1,000	yds/lb mg/m	JISR 7601

5900 88th Street
 Sacramento, CA
 95828, USA
Tel: 916.386.1733
Fax: 916.383.7668
Web: www.grafil.com



ISO 9001:2008
 FM 56416

03/2010

6, Orchard Court
 Binley Business Park
 Harry Weston Road
 Binley, Coventry CV3 2TQ UK
Tel: +44 (0) 2476 447272
Fax: +44 (0) 2476 449565